



OAK SUPAI

This 3-strip stained oak floor from the Tres Collection features a strikingly rich dark brown finish, resulting in an elegant and refined expression. The silk lacquer finish gives the floor a polished appearance bringing out the natural character of the timber. The even finish protects the wood from daily wear, without adding artificial shine.

PRODUCT DETAILS

Article Number	133NABEK5LUW 0
EANCode	7393969034135
Surface treatment	Silk lacquer
Dimensions	2423 x 200 x 13 mm
Weight per Package x	24.5 kg
Area per Package (m²)	3.4
AreaPerPalletM2	170
Package info	Packages may contain start and stop boards.

DETAIL DESCRIPTION

Naturally occurring wood colour variations allowed, from light to dark brown. Sapwood will occur. The product includes medium sound and black knots. Knots may vary in size and numbers.

COLOUR CHANGE

Stained product - noticeable color change over time.

FACTS

Wood Species	Oak
Board	3-strip
Range	Kährs Avanti
Collection	Tres Collection
Resandable	2-3 times
Natural/Stained	Stained
Brinell Value	3,7
Joint	Woodloc® 5S
Floor heating	Yes
Warranty	20 years
Wear-layer material	Hardwood
Wear-layer thickness	2.6 mm
Core material	Pine/Spruce lamella
Thickness	13 mm
Surface Colour	Dark Brown 5L

TECHNICAL PROPERTIES

TestMoistureContent	7%±2%
TestMinimunMeanDensity	>500 kg/m³
TestReactionToFire	Dfl-s1
TestFormaldehydeEmission	E1
TestContentPCP	≤ 5 x 10-6n
TestBreakingStrength	NPD
TestThermalConductivity	0,14 W/mK
TestThermalResistanceRValue	.09 (m2K/W)
TestBiologDurability	Class 1
TestCarb2	Compliant



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.